




CONTI-AIR®
BLANKET TECHNOLOGY

CONTI-AIR® LITHO 3


Sheetfed All-Purpose Blanket



CONTI-AIR® LITHO 3



Coldset



Heatset



Sheetfed



Packaging



Metaldeco

Das weiterentwickelte Litho 3, mit neuer Karkasse und 2 integrierten, aufeinander abgestimmten, kompressiblen Schichten.

- › Neue stabile 3-Lagen Karkasse mit deutlich geringer Dehnung, dadurch jetzt auch geeignet für den Bogenoffset im Grossformat
- › Ausgerüstet mit der bewährten Litho Deckplatte für scharfen Raster- und besonders ruhigen Vollflächendruck
- › Sehr gut im Akzidenzdruck einsetzbar
- › Hervorragende Knautscherbeständigkeit durch 2 aufeinander abgestimmte kompressible Schichten

The further developed Litho 3, with a new carcass and 2 integrated, harmonized, compressible layers.

- › Newly durable 3-ply carcass with significant reduced elongation, as a result it suits also to big format size sheetfed presses
- › Equipped with the approved Litho top surface for a good dot sharpness and smooth printing of solids
- › Highly suitable for commercial print
- › Excellent smash resistance due to 2 harmonized compressible layers


Norm / Standard		
Farbe: Color:	ozeanblau ocean blue	
Oberfläche: Surface:	feinstgeschliffen microground	
Härte Deckgummi: Hardness of face compound:	63 Shore A	DIN ISO 48-4*/**
Kompressibilität bei 1.350 kPa: Compressibility at 1.350 kPa:	0,220 mm	R_05_10AA3119*
Nenndicke: Thickness:	1,96 mm +/-0,02 mm	DIN EN ISO 2286-3*

* In Anlehnung an die gegebene Norm durchgeführt. Bitte beachten Sie, dass die Anzahl der getesteten Stichproben variieren kann.
Performed in accordance with the given standard. Please note that the number of samples tested may differ.

** Die ausgewiesene Härte für das Deckplattengummi kann nur an Prüfkörpern die der Norm entsprechen gemessen werden.
The specified hardness of the cover compound can only be measured using test samples according to the standard. It is not possible to measure the hardness directly on the product itself.

Unsere Drucktücher verfügen über eine spezielle CONTI-AIR® kompressible Schicht geschlossener Mikrozellen mit Überdruck.

Our printing blankets have a special CONTI-AIR® compressible layer of overpressured microcells.



ContiTech Elastomer-Beschichtungen GmbH
Breslauer Str. 14 | 37154 Northeim | Germany
service@contiair.com
www.contiair.com

The content of this publication is not legally binding and is provided as information only. The trademarks displayed in this publication are the property of Continental AG and/or its affiliates. Copyright © 2023 ContiTech AG, Hanover. All rights reserved. For complete information go to: www.continental-industry.com/disclosure

Der Inhalt dieser Druckschrift ist unverbindlich und dient ausschließlich Informationszwecken. Für weitere Informationen besuchen Sie bitte: www.continental-industry.com/disclosure