

PRODUCT DATA SHEET

SP 1504 Easy Apply™

Issued: 10/2024

Introduction

The Avery Dennison® SP 1504 Easy Apply™ is a gloss white, premium quality self-adhesive PU blend. The film is highly conformable and opaque, and offers excellent durability. Combined with a SL 6460 overlamine, it is a wrapping film highly recommended for challenging applications such as rivets and corrugations. In addition, SP 1504 features the Easy Apply™ technology with an air-egress feature, and in combination with a low initial tack, it allows for easy repositioning. Having a face film based on PU blended material, it offers a PVC-free alternative to traditional vinyl films, containing no chlorine, phthalates and other halogens, reducing emissions of volatile organic compounds (VOCs).



Face Film

60 micron gloss white PU blend



Adhesive

Permanent, grey acrylic based



Backing

Easy Apply™ Two side PE coated StaFlat™ paper, 145g/m2



Durability

10 years (unprinted, vertical exposure)



Shelf Life

2 years

Conversion

SP 1504 Easy Apply is a premium product, delivering excellent durability for a wide range of graphics applications. The film is suitable for use on a variety of super-wide format inkjet printers using solvent, eco solvent, UV or latex inks.

To enhance colour and to protect images against UV radiation and abrasion, it is recommended to protect Avery Dennison SP 1504 Easy Apply using an overlamine - Avery Dennison SL 6460 Gloss conformable overlamine.

For more details and recommended combinations of SL films and media, please refer to "Technical Bulletin 5.3 - Recommended combinations and durability of Avery Dennison MPI/SP and Avery Dennison DOL/SL Series Films". For detailed information on how to apply the product, please refer to "Technical Bulletin 5.10 - Application of Avery Dennison PVC-free Wrapping Film".

Recommendations

- » Large fleet graphics on flat, curved, riveted and corrugated surfaces
- » Vehicle wrapping applications
- » Interior & exterior signs
- » Durable advertising

Features

- » PU blended face film, offering a PVC-free alternative to traditional vinyl films
- » Superb 3D conformability for demanding vehicle and fleet wrapping projects
- » Easy installation due to great repositionability
- » Stunning and consistent image quality on a variety of printers using solvent, eco-solvent, UV or latex inks
- » Long outdoor durability, up to 10 years unprinted
- » ICS Performance Guarantee
- » HP Latex Certified

Physical Characteristics

	Test method ¹	Results
Product		
Caliper, facefilm (micron)	ISO 534	60
Caliper, facefilm + adhesive (micron)	ISO 534	90
Opacity		>99%
Dimensional stability (mm max.)	FINAT FTM 14	0.4
Shelf life (years)	Stored at 22° C/50-55 % RH	2
Durability ² (years)	Vertical exposure	10
Fire Classification	EN13501-1	B-s1,d0
Adhesive		
Elongation (%)	ISO-527-3	> 150
Adhesion, initial (N/m)	FINAT FTM-1, stainless steel	450
Adhesion, after 24 hours (N/m)	FINAT FTM-1, stainless steel	550
Temperature range		
Application temperature (Minimum: °C)		≥10 °C
Service temperature (°C to +°C)		- 40 °C to + 80 °C
Chemical properties³		
Chemical resistance	Mild acids	No effect

Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

2) Durability: The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased..

3) Prolonged immersion in gasoline and similar fluids is not recommended.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.